

Sulfate-resistant, polymer-modified special mineral slurry for exterior and interior renovation and sealing works

Characteristics

INTRASIT® DS1 54Z is an easy-to-apply, cement-bound repair slurry with a high sulfate resistance. Sealings made of **INTRASIT® DS1 54Z** are highly impervious and mechanically strong and are resistant to mechanical stress and chemical attacks, e.g. de-icing salts, faeces and aggressive substances which are usually present in the soil.

- Sulphate-resistant
- Frost-resistant
- Waterproof
- Reinforced with polymers
- Permits diffusion

Use

INTRASIT® DS1 54Z is used to seal building parts in contact with the soil against ground moisture, non-pressing surface water, seepage water and waste water, and also for waterproofing tanks or containers of max. 5 m depth of water. Used in conjunction with **INTRASIT® VK 10A** for subsequently waterproofing and renovation of moistly and salt damaged undergrounds, at the positive and negative sides until 15 m head of water. For vertical and horizontal exterior and interior surfaces and for prepared and non-shrinking substrates.

Areas of application:

- Washrooms, bathrooms, showers, etc.
- Silos, waster water treatment plants, shafts
- Plinths
- Concrete, screed, masonry
- Subsequently waterproofing in- and outdoor

Specifications

Presentation	paper sack
Container size	25 kg
Delivery quantity	30 containers per pallet
Color	grey
Fresh mortar density	approx. 1.68 kg/l
Working temperature	+2 °C to +30 °C
Workable time	approx. 30 minutes
Rainproof	after about 4 hours
Foot traffic	after about 8 hours
Coatable	after about 7 days
Water vapor-diffusion resistance index μ	approx. 100
Water imperviousness after 28 days of submersion	about 1.5 bar
Bending tensile strength after 28 days	approx. 6 N/mm ²
Compressive strength after 28 days	approx. 28 N/mm ²
Adhesive tensile strength after 28 days	approx. 1.5 N/mm ²
Storage	dry, 6 months

Quantity req. / thickness of layer

Ground moisture	approx. 3 kg/m ² corresponding to 2.0 mm
Non-pressing water	approx. 4 kg/m ² corresponding to 2.5 mm
Water tanks (depth of water 5 m)	approx. 5 kg/m ² corresponding to 3.0 mm

Preparation of the surface

The substrates must be firm, even, resilient, free of frost, dust, dirt and plaster.

Pre-wet absorbent bases well, so that no moisture is leached from the sealing slurry. The surfaces to be sealed must be free of cracks; if necessary, chisel out cracks and fill with cement mortar or inject resin. Make good any faults, render over rock pockets. Repoint mortar in brickwork, if necessary. With irregular brickwork with numerous bumps and hollows, apply a leveling coat of **INTRASIT® SM 54Z**.

Break all edges under 45° or bevel (bevel width ≥ 3 cm). Round out all corners with coving of at least 3 cm. For critical wall and floor slab sealings outdoors and indoors, e.g. if the reverse side is damp and/or damaged by salt, use in combination with **INTRASIT® VK 10A**.

Application

Guidelines are DIN 1053 for masonry and DIN V 18550 for plaster, and also hahne's brochure "INTRASIT® remedial interior basement wall repair".

1. Slowly pour **INTRASIT® DS1 54Z** into clear water in a clean mixing container while stirring it well until you have a smooth texture without any lumps. Recommended mixing ratio for brushing and slurry:
1 part by volume water : 3 - 3.5 parts by volume **INTRASIT® DS1 54Z**
or 1 part water : 4 parts powder
2. Brush the slurry on with a wide brush in at least 2 sessions. Apply the first coat thickly, covering the substrate fully. Apply the second coat after approx. 6 hours but no later than 24 hours.
If **INTRASIT® VK 10A** is also used for sealing, apply two layers of the sealing slurry alternating with the silicifier while still wet (starting with **INTRASIT® VK 10A**).
3. To accelerate the hardening process on very damp substrates, you can mix **INTRASIT® DS1 54Z** with **INTRASIT® RASANT 55Z**.
Recommended mixing ratio:
3 : 1 to 1 : 1 part by weight
4. Clean all processing equipment with water immediately after use. Hardened material can only be removed mechanically.

Precautions

After hardening, **INTRASIT® DS1 54Z** must be protected from damage (plaster, screed, tile covering, drainage tiles, etc.) and from drying out too quickly (keep damp for at least 24 hours).

hahne system products

INTRASIT® VK 10A
INTRASIT® Rasant 55Z

Important notes

- Observe the working temperature of +2 °C to +30 °C.
- Do not penetrate the sealing with nails or dowels.
- Do not mix with other building materials.

Ingredients

Standard cements, mineral aggregates, additives, special additives, sealant

Safety provisions/recommendations

Contains cement and will cause alkaline reactions when it comes into contact with moisture or water.

For detailed information regarding safety during transport, storage and handling, refer to the updated safety data sheet.

Disposal

The local waste removal regulations must be observed.

Manufacturer

Heinrich Hahne GmbH & Co KG
Heinrich-Hahne-Weg 11
D-45711 Datteln

This information is based on extensive tests and practical experience. However, it cannot be applied to every type of application. If in doubt, we recommend that you test the product before using it. Due to continuous product improvement, this information is subject to change without notice. Our General Terms and Conditions apply. Version as of 6.2014